

✓  
OFFICE OF NAVAL RESEARCH

Contract N00014-76-C-0200

Task Number NR 356-504

TECHNICAL REPORT NO. 14

A WATER-SENSITIVE THERMOMECHANICAL  
TRANSITION IN A POLYIMIDE

by

*Checked DDC  
no. 900 70*

Y. Ozari, R. H. Chow and J. K. Gillham

to be published in

JOURNAL OF APPLIED POLYMER SCIENCE

Polymer Materials Program  
Department of Chemical Engineering  
✓Princeton University  
Princeton, N. J. 08540

February 1978

Reproduction in whole or in part is permitted for any purpose  
of the United States Government

Approved for Public Release. Distribution Unlimited

J. K. Gillham  
Principal Investigator  
609/452-4694

DTIC QUALITY INSPECTED 1

19960223 060

PLASTEC  
29420

A WATER-SENSITIVE THERMOMECHANICAL  
TRANSITION IN A POLYIMIDE

Y. Ozari, R. H. Chow and J. K. Gillham

Polymer Materials Program  
Department of Chemical Engineering  
Princeton University  
Princeton, New Jersey 08540

SYNOPSIS

The effect of water vapor on a polyimide has been investigated in the temperature region  $-190^{\circ}$  to  $325^{\circ}\text{C}$  using an automated torsion pendulum. A damping peak " $T_{\text{H}_2\text{O}}$ " develops at  $-122^{\circ}\text{C}$  (1 Hz) in the thermomechanical spectra of the polymer which is due to water-polymer interactions. The peak intensifies as the humidity of the conditioning atmosphere, at both  $30^{\circ}\text{C}$  and at  $325^{\circ}\text{C}$ , increases and attains a limiting value at about 2000  $\text{ppm}_v \text{H}_2\text{O}$ . The process is reversible. It is concluded that the number of sites in the polymer for interaction with water is low and limited ( $\approx 0.3$  molecules  $\text{H}_2\text{O}$  per polymer repeat unit) and, assuming direct proportionality between the intensity of the loss peak and the amount of water adsorbed, that the adsorption of water vapor follows the Langmuir isotherm. (Author).

## INTRODUCTION

Water molecules associate strongly with polar polymers through hydrogen bond formation (1), the exothermic heat of formation of which is in the range 3.4 to 6.6 Kcal/mole (2-4).

Recent publications (5, 6) have reported that a water sensitive damping peak " $T_{H_2O}$ " appears in the thermomechanical spectra of polyimides obtained using the torsional braid analysis (TBA) technique (7). This damping peak is in the temperature range  $-90^\circ$  to  $-120^\circ\text{C}$  and varies with the molecular structure of the polyimides (6). In epoxy systems (8, 9),  $T_{H_2O}$  appears at higher temperatures (ca.  $-70^\circ\text{C}$ ) on the shoulder of a glassy state transition ( $T_{\text{sec}} = \text{ca. } -90^\circ\text{C}$ ); both transitions are coupled. The  $T_{H_2O}$  damping peak in polymethylmethacrylates (10,11) at ca.  $-100^\circ\text{C}$  is also on the shoulder of a glassy state transition [ $T_{\text{sec}} = 24^\circ\text{C}$  (1.24 Hz)] and increases in intensity with the humidity level of the conditioning atmosphere. In polyaminoacids (12), two types of  $T_{H_2O}$  peaks were reported, at  $-120^\circ$  to  $-130^\circ\text{C}$  and at  $0^\circ$  to  $35^\circ\text{C}$ . Table 1 summarizes results obtained earlier in this laboratory. The effect of water on natural products, such as lecithin and human erythrocyte ghosts, has been investigated elsewhere using TBA (13). High amounts of water in these materials (66-100%) produced large differences between the wet and dry materials; distinct peaks developed in the vicinity of  $-120^\circ$ ,  $-25^\circ$  and  $35^\circ\text{C}$  due to the presence of water.

Since the locations of  $T_{H_2O}$  varies with polymer structure, it may be concluded that the relaxations are due to specific associations of water molecules with polymeric materials and not merely to condensation of water on the surface of the materials.

The particular polyimide system examined in this work (Fig. 1) is especially suitable for investigating the water vapor effect since the  $T_{H_2O}$  damping peak is isolated from  $T_{sec}$  and is symmetric.

Linear aromatic polyimides are formed usually from the reactions of dianhydrides of tetracarboxylic acids with diamines. When the dianhydride is treated in solution with the diamine at room temperature, a polyamic acid is formed; heating yields the polyimide (imidization). If the polyamic acid formation stage is undesirable, a tetraacid can be used in place of dianhydride; the two stages of the reaction then occur together by heating or by adding another anhydride (usually acetic anhydride) to the reaction mixture (Fig. 1). The high glass transition temperatures of the high temperature polyimides, the low extents of softening which occur through their glass transition temperatures, and the thermal reactions which stiffen the materials on heating above the glass transitions, prevent processing by conventional thermoplastic methods. They are therefore formed in the fabrication process from reactive precursors, imidization being completed *in situ*.

The current report deals with a recently introduced commercial system (duPont NR-150A2) which is outlined in Fig. 1 (14). In particular, an attempt has been made to correlate the intensity of the  $H_2O$  damping peak of the polyimide to the level of water vapor and to the temperature of the conditioning atmosphere.

## EXPERIMENTAL

### Materials and Sample Preparation

The precursor solution was made from a stoichiometric mixture of the 6F tetraacid [2,2-bis(3',4'-dicarboxyphenyl) hexafluoropropane] and 4,4'-oxydianiline dissolved in a 3:1 mixture by weight of N-methyl pyrrolidone and ethanol. A composite specimen of polymer precursor and glass braid was utilized for the torsion pendulum studies. After mounting a solution-impregnated braid, solvent was removed from the specimen and the imidization reactions were completed in the TBA apparatus *in situ* in He by heating the specimen to 325°C for 5 hours. After cure, the composite specimen contained 48% by weight of polymer. The intrinsic viscosity of such a polymer in H<sub>2</sub>SO<sub>4</sub> (conc.) at 25°C is about 0.8 dl/g (14, 15).

### Instrumentation and Data Representation

TBA: Thermomechanical TBA spectra were obtained using a fully automated torsion pendulum analysis system (7, 16, 17, 18). A hard-wired analog computer (data reducer) (17, 18) provided automatic alignment of the transducer, initiation of oscillations of the pendulum, printing of the values of the temperature (mV, from an iron-constantan thermocouple), period (P in sec.) and logarithmic decrement ( $\Delta$ ) of the damped oscillations. [ $\Delta = (1/n) \ln (A_i/A_{i+n})$ , where  $A_i$  is the amplitude of deformation of the  $i$ th oscillation and  $n$  is the number of oscillations between two fixed arbitrary boundary amplitudes in each wave]. The reduced data were also presented on an XY recorder versus the temperature (or time) as the logarithm

of the relative rigidity ( $1/P^2$ ) [which is a good approximation (19) for the relative elastic shear modulus ( $G'$ )] and the logarithm of  $\Delta$ .

Constant and different levels of water vapor in the atmosphere were obtained by mixing wet and dry gas streams of He (8). The levels of water were measured by an electronic hygrometer in the outlet port of the apparatus and ranged from 20 to 10,000 ppm<sub>v</sub> (parts per million on a volume basis) of H<sub>2</sub>O in He.

TGA and DTA measurements were recorded on a duPont 950 Thermogravimetric Analyzer and on a duPont 900 Differential Thermal Analyzer. The precursor solution was used "as received".

### Experiments

TBA: A single specimen was used. The uncured specimen was heated to 325°C at a rate of 1.5°C/min (the rate used in all the TBA experiments) and post-cured by continued heating for 5 hours at 325°C in 20 ppm<sub>v</sub> H<sub>2</sub>O/He in order to provide a specimen which would be chemically inert at 325°C. A spectrum of the "dry" specimen was then recorded on decreasing and then on increasing the temperature (325° → -190° → 325°C) in order to check reversibility of the data. The specimen was conditioned at 325°C at a constant level of water vapor for a measured time and the spectrum was recorded, using the same input atmosphere used for conditioning, again in the two directions of change in the temperature (325° → -190° → 325°C) in order to investigate hysteresis phenomena (including the effect of condensation of water on the specimen). The specimen was cooled to 30°C, conditioned at the same level of water vapor and period of time and then a plot was taken (30° → -190°C → 30°C) again using the input atmosphere used for conditioning the specimen. The temperature was then increased to 325°C and a new cycle

with a different level of water vapor was undertaken.

Below 0°C water freezes on the walls of the apparatus, and the level of water vapor in the atmosphere around the specimen decreases (Fig. 2). However, the amount of trapped water in the polymer remains unchanged (8). As the temperature is raised through 0°C the condensed water evaporates thus increasing the level of water in the atmosphere; at higher temperatures it decreases to the original level. Since the polymer was exposed to high humidity during this process, the specimen was heated to 325°C in order to eliminate water prior to reequilibration with a different level of water vapor.

TGA: Prepolymer solution (~ 8 mg) was used "as received". The relative weight was recorded versus temperature to 325°C in N<sub>2</sub> (5 ppm<sub>v</sub> H<sub>2</sub>O). At 325°C, an isothermal experiment was run for 135 min. and then the sample was heated to 750°C (Fig. 5,  $\Delta T/\Delta t = 5^\circ\text{C}/\text{min}$ ).

## RESULTS AND DISCUSSION

### Cure

The thermomechanical data of Fig. 3 show the changes which occur on heating the unreacted "as received" material to 325°C. It is evident that the removal of solvents and the imidization reaction proceed rapidly in the vicinity of 170°C. This is in accord with other experiments (14, 15).

After the above cure, the transitions were (Fig. 3):  $T_g = 313^\circ\text{C}$  (0.62 Hz),  $T_{\text{sec}} = 135^\circ\text{C}$  broad (1.0 Hz),  $T_{\text{H}_2\text{O}} = -117^\circ\text{C}$  (1.1 Hz). The latter ( $T_{\text{H}_2\text{O}}$ ) relaxation is not observed after post-curing at 325°C for 5 hours in a dry atmosphere (20 ppm<sub>v</sub> H<sub>2</sub>O/He) (Fig. 4), but reappears after exposure to water vapor (Fig. 6). After the post-cure, the  $T_g$  had risen to 319°C (0.61 Hz)

but  $T_{\text{sec}}$  was unchanged. Another glassy state relaxation,  $T < -190^{\circ}\text{C}$ , is apparent in the dry material (Fig. 4). Hysteresis is observed immediately below  $T_g$  (Fig. 4).

The reported  $T_g$  [ $285^{\circ}\text{C}$  (14)] is lower than the present results due to the undercure of the different thermal treatments. TGA experiments (Fig. 5) show that a small loss of weight occurs particularly during the first 2 hours of postcure at  $325^{\circ}\text{C}$ . The polymer is then stable to above  $500^{\circ}\text{C}$ .

The thermomechanical behavior of the polyimide is consistent with previous investigations (5, 6). As expected, the damping curve of the polyimide is similar to those of polyimides derived from benzophenone tetracarboxylic acid and from  $[(\text{COOH})_2\text{C}_6\text{H}_3]_2\text{Si}(\text{CH}_3)_2$  with 4,4'-oxydianiline (Table 2, polymers 3 and 4). In these three cases the spectra consist of sharp  $T_g$  and broad  $T_{\text{sec}}$  transitions. Although  $T_g$  depends on the specific structure of the polymer, the ratio  $T_{\text{sec}}/T_g$  ( $^{\circ}\text{K}/^{\circ}\text{K}$ ) is unchanged (0.68 - 0.70) for both the reported and for the present work. A water-sensitive loss peak in the vicinity of  $-100^{\circ}\text{C}$  is also observed in the three polymers.

Incorporation of the perfluoroisopropylidene group between the aromatic rings results in increased chain flexibility over that of pyromellitic dianhydride (PMDA). However, motion between the two aromatic rings of the tetraacid is restricted by the trifluoromethyl groups in comparison with the effect of the carbonyl and  $\text{Si}(\text{CH}_3)_2$  linkages. The result is a higher  $T_g$  than for polymers 3 and 4, but lower than for the more rigid polymer 1 (Table 2).



### Effect of Water

When water vapor is introduced in the atmosphere a " $T_{H_2O}$ " peak at  $-122^\circ \pm 2^\circ\text{C}$  (1.0 -1.1 Hz) emerges in the polyimide spectra<sup>(e.g. Fig. 6)<sup>2</sup></sup>. According to previous publications (5, 6),  $T_{H_2O}$  appears in polyimide spectra even when the atmosphere is "dry". Water elimination was effected in some of the polymers only when the polyimide was heated overnight at  $130^\circ\text{C}$  (i.e. below  $T_g$ ) (e.g. Table 1, polymer 1). Drying could be accomplished with the presently examined polyimide only by heating above the  $T_g$  of the polymer [where diffusion is facilitated (20)].

Experimental results showing the  $T_{H_2O}$  transition versus level of water vapor in the conditioning atmosphere at  $30^\circ\text{C}$  are summarized in Fig. 7 and Fig. 8. (The time for equilibration was found to be less than 1 hour at  $30^\circ\text{C}$ .) The peak is isolated from  $T_{sec}$  and does not affect  $T_g$  and  $T_{sec}$ . Since it is also symmetric and its location is not affected by its intensity (Table 3), the observance of its change as a function of the external humidity is simplified. Its intensity reaches a limiting value in the vicinity of levels of 2000 ppm  $H_2O$ .

When a humid atmosphere is introduced into the TBA apparatus at temperatures below the frost point of water (on heating or cooling),  $T_{H_2O}$  does not appear (8, 9). Thus, it is concluded that  $T_{H_2O}$  is due to polymer-water interactions and not simply to an intrinsic property of condensing water. This interaction is probably caused by hydrogen bonding (which is observed in the IR spectra of the polyimide (15)).

The maximum capacity of water in the polymer, assuming five binding sites per repeat unit, is 12.9% (wt. water/wt. "moist" polymer). The actual take-up of water in the plateau region after conditioning at  $30^\circ\text{C}$

was found to be less than 1% by weight measurement. This low water absorption agrees with results of other workers (14, 15). The low pick-up of water is related to the hydrophobic character of the polymer which contains six fluorine atoms and four aromatic groups in each repeat unit. The reversibility of the water effect is apparent from a comparison of Figures 9 and 4. When the polymer was dried, the peak at  $T_{H_2O}$  diminished almost to the original intensity.

From the present results it is difficult to conclude whether the effect is a surface or a bulk phenomenon. Nevertheless, two observations support the nature of water diffusion in bulk:

a) The time (5 hr) needed to dry the polymer and the necessity to heat it above  $T_g$  (325°C) for that purpose.

b) When the polyimide was fabricated with a low void content (low surface area) no marked differences in the water content were observed (14).

Two different temperatures for conditioning were chosen, one above the glassy state (325°C) and one close to room temperature (30°C). The specimen was conditioned at the desired level of water vapor and temperature for one hour. Longer times (5 hr) did not affect the results. As is seen in Fig. 8, larger values of  $\Delta$  were obtained at 30°C than at 325°C for low levels of water vapor (up to ca. 2000 ppm  $H_2O/He$ ). At higher levels of water vapor, the same plateau value for  $\Delta$  was reached for both temperatures. Since the equilibration time is relatively short, a reequilibration occurs as the temperature decreases to 30°C during the thermomechanical experiment. Therefore the real difference of the water pick up at these two temperatures should be higher than that observed. The additional thermal hysteresis in (cf. Fig. 4 and Fig. 6) the temperature region 190°C to 280°C  $\Delta$  provides supporting evidence for polymer-water interactions, even in the high temperature region. Because of the low pick-up of water and the low retention of it at high temperatures,

no significant decrease of  $T_g$  could be observed on account of plasticization by water.

In previous investigations on epoxy systems (8), it has been shown that higher absorbance of water at low temperatures, as in the present system, supports a theory of bond formation between water and the polymer rather than simple mixing. According to a parallel approach, the free water molecules in the external atmosphere are in equilibrium with the bound water. Since the formation of hydrogen bonds is an exothermic process, the value of the equilibrium constant ( $\alpha$ ) is decreased by increasing temperature ( $d\ln\alpha/dT = \Delta H/RT^2$  where  $\Delta H$  is the heat of interaction). A decrease in  $\alpha$  at higher temperatures leads to a decrease in the equilibrium conversion, which leads to a lower pick-up of water, as was obtained.

The plateau value of  $\Delta$  (Fig. 8), which is reached at relatively low levels of water vapor (ca. 2000 ppm), and the small change in the value of  $1/P^2$  (Fig. 7) (the relative value of  $1/P^2$  is dependent on the dimensions of the specimen) indicate that at high humidity there is no significant change in the mass of the specimen -- implying that the observed  $T_{H_2O}$  is not due to water condensed on the polymer.

Thermal hysteresis develops in the temperature range  $-45^\circ$  to  $20^\circ\text{C}$  at low levels (180 ppm) and shifts up to from  $4^\circ$  to  $77^\circ\text{C}$  at higher levels (10,000 ppm) of water vapor. A significant change in values of  $\Delta$  is also observed, i.e., 0.02545 ( $-4^\circ\text{C}$ , 1.07 Hz) for the former and 0.04495 ( $52^\circ\text{C}$ , 1.02 Hz) for the latter. As it can be seen from Fig. 6, small changes in the values of  $1/P^2$  exist in this region which depend on the direction of temperature change. The hysteresis loop differs from  $T_{H_2O}$  (Table 3) in that it increases with the humidity level without reaching a limit, and it is coupled with the water flash-off from the apparatus (Figs. 2 and 6). There-

fore, it is concluded that this hysteresis is due to plasticization of the polymer by water. The shift in the hysteresis region results from elimination of the plasticizing water which occurs at higher temperatures for higher levels of water vapor in the atmosphere.

That the  $T_{H_2O}$  transition of the polyimide occurs at a lower temperature ( $-122^\circ\text{C}$ ) than for polymethylmethacrylate ( $-100^\circ\text{C}$ ) suggests that the water bound to a polar site in the rigid polyimide backbone moves more readily (i.e. at lower temperatures) than when bound to the polar site of the ester side group. In polyimide, the water transition is not coupled to an obvious secondary relaxation of the polymer whereas it is presumably coupled to the motions of the ester group in polymethylmethacrylate.

In order to investigate the effect of water vapor on the polyimide quantitatively, the external humidity was increased incrementally and the development of the thermomechanical spectra was followed. A plot of  $\Delta$  at the maximum of  $T_{H_2O}$  vs. the humidity level expressed as  $\text{ppm}_v H_2O$  in He (Fig. 8), is similar to the plot of amount of gas adsorbed vs. its pressure for the case of one molecule occupying a single site (21, 22).

Assuming that  $\Delta$  at the peak is proportional to the volume fraction of the lossy part of the solid (23), and using the direct proportionality of level of water vapor ( $\text{ppm}_v H_2O/\text{He}$ ) to the partial vapor pressure of water in the gas mixture, Langmuir's equation (21) should be applicable:

$$p/\theta = \frac{1}{a} + p$$

Here,  $p$  is the gas pressure,  $\theta$  the fraction of the occupied sites and  $a$  is a factor which is considered to be dependent on the temperature alone and is defined as follows:

$$1/a = (K/\delta \sqrt{2MkT}) e^{-q/RT}$$

In this, K is a velocity constant of desorption,  $\delta$  is a probability factor, M is the molecular weight of the adsorbed species, k is the Boltzman constant, T is the temperature in °K, q is the heat of adsorption per gram molecule and R is the gas constant.

If  $(\Delta - \Delta_o)$  (for the same specimen) is linearly dependent on the water concentration in the polymer, as assumed, then

$$\theta = \frac{\Delta - \Delta_o}{\Delta_{\max} - \Delta_o}$$

where  $\Delta_o$  and  $\Delta_{\max}$  are the minimum and the maximum values of  $\Delta$  at  $T_{H_2O}$ , respectively.

A plot of  $H/\theta$  vs. H (humidity level; ppm<sub>v</sub>) gives a straight line (Fig. 10) with slope 45°, as expected. The increase of the intercept with the temperature also agrees with the anticipated behavior of  $1/a$ .

#### CONCLUSIONS

The present investigation demonstrates the utility of the TBA method in detecting the presence of small amounts of water in polyimide systems. More specific correlations between the peak intensity location (temperature) and molecular architecture of polymers will be sought using systematic series of polymers and reactants.

ACKNOWLEDGMENTS

Dr. H. H. Gibbs of duPont is acknowledged for providing the prepolymer solutions and for discussions of results. Financial support was provided by the Chemistry Branch of the Office of Naval Research.

REFERENCES

1. J. A. Barrie in "Diffusion in Polymers", J. Crank and G. S. Park, Editors, Academic Press, London and New York (1968), Chapt. 8.
2. A. W. Searcy, J. Chem. Phys., 17, 210 (1949).
3. M. Gordon, C. S. Hope, L. D. Loan and R-J. Roe, Proc. Royal Soc., A258, 215 (1960).
4. G. C. Pimentel and A. L. McClellan, "The Hydrogen Bond", p. 212, W. H. Freedman and Co., London (1960).
5. J. K. Gillham, K. D. Hallock and S. J. Stadnicki, J. Appl. Poly. Sci., 16, 2595 (1972).
6. J. K. Gillham and H. C. Gillham, Polym. Eng. Sci., 13 (6), 447 (1973).
7. J. K. Gillham, A.I.Ch.E. Journal, 20(6), 1066 (1974).
8. J. K. Gillham, C. A. Glandt, and C. A. McPherson, in "Chemistry and Properties of Crosslinked Polymers", S. S. Labana, Editor, Academic Press, New York (1977), p. 491.
9. J. K. Gillham, Preprints, p. 14, Society of Plastics Engineers, National Technical Conference, "High Performance Plastics", Cleveland, Ohio. Oct. 5, 1976.
10. N. G. McCrum, B. E. Read and G. Williams, "Anelastic and Dielectric Effects in Polymeric Solids," Wiley, New York, 1967, Chapt. 8.
11. J. K. Gillham, S. J. Stadnicki, and Y. Hazony, J. Appl. Poly. Sci. 21, 401 (1977).
12. R. R. Krug and J. K. Gillham, J. Appl. Polym. Sci., 17, 2089 (1973).
13. W. M. Wong and P. H. Geil, Department of Macromolecular Science, Case Western Reserve University, Cleveland, Ohio 44106, T. R. No. 267, June, 1974.

14. H. H. Gibbs and C. V. Breder, *Advances in Chemistry Series*, 38 (142), 442 (1974).
15. H. H. Gibbs, private communication.
16. J. K. Gillham, *CRC Critical Reviews in Macromolecular Science*, 1, 83 (1972).
17. C.L.M. Bell, J. K. Gillham and J. A. Benci, *Am. Chem. Soc., Poly. Preprints*, 15(1), 542 (1974).
18. C. L. M. Bell, J. K. Gillham and J. A. Benci, *Soc. Plastics Engineers, Annual Tech. Conf., San Francisco, Cal., SPE Tech. Papers*, 20, 598 (1974).
19. S. J. Stadnicki, J. K. Gillham and Y. Hazony, *Amer. Chem. Soc., Polym. Preprints*, 15(1), 556 (1974).
20. Ref. 1, page 282.
21. D. O. Hayward and B.M.W. Trapnell, "Chemisorption", Chapt. V. Butterworths and Co., London, 2nd Edition (1964).
22. S. Brunauer, L. E. Copeland and D. L. Kantro in "The Solid-Gas Interface", E. A. Flood, Editor, Marcel Dekker, Inc., N. Y. (1967), Vol. 1, Chapt. 3.
23. Ref. 10, page 139.



TABLE CAPTIONS

Table 1.  $T_{H_2O}$  transitions of polymers.

Table 2. Transition temperatures of polyimides.

Table 3.  $T_{H_2O}$  transition at different humidity levels after conditioning at 30°C.

FIGURE CAPTIONS

Fig. 1. Synthesis of Polyimide.

Fig. 2. Temperature and humidity level (expressed as parts per million of water in helium on a volume basis) for a constant adjustment of the humidity system vs. time in the TBA system.

Fig. 3. Thermomechanical spectra of polyimide precursor (30°C → 325°C) and polyimide (325°C → -190°C → 140°C).

Fig. 4. Thermomechanical spectra of polyimide after conditioning in a dry atmosphere.

Fig. 5. Thermogravimetric analysis of polyimide.

Fig. 6. Thermomechanical spectra of polyimide after conditioning in a humid atmosphere.

Fig. 7.  $T_{H_2O}$  transition after conditioning at 30°C at different humidity levels.

Fig. 8.  $\Delta$  at  $T_{H_2O}$  vs. humidity level of conditioning atmosphere at 30°C.

Fig. 9. Thermomechanical spectra of polyimide dried after conditioning in the sequence of humid atmospheres used in the experiments.

Fig. 10. Langmuir plots of  $H/\theta$  vs.  $H$ .

TABLE 1.  $T_{H_2O}$  Transitions of Polymers













No.	STRUCTURE		$T_{H_2O}$ [°C]	Reference
	Dianhydride	Diamine		
1			-80 (0.50 Hz)	7
2			-122 (1.01 Hz)	Present Investigation
3			-100 (0.90 Hz)	7
4			-100 (0.95 Hz)	7
5			-90 (0.88 Hz)	7
6			-100 (0.95 Hz)	7
7			-120 (0.96 Hz)	7
8			-100 (0.86 Hz)	7
9	Polymethylmethacrylate (atactic)		-103	12,21
10	Epoxies		-90	10
11	Polyaminoacids		-120 -130, 0-35	14

TABLE 2. Transition Temperatures of Polyimides.






No.	STRUCTURE		TRANSITIONS				Ref.
	Dianhydride	Diamine	T <sub>g</sub> (°C)	T <sub>sec</sub> (°C)	T <sub>sec</sub> /T <sub>g</sub> (°K/°K)		
1			> 330	? 210	< 0.80		7,8
2			319	140	0.70		Present Investigation
3			283	112	0.69		7,8
4			271	94	0.68		7,8

TABLE 3

$T_{\text{H}_2\text{O}}$  Transition at Different Humidity Levels  
after Conditioning at 30°C.

<u>ppm<sub>v</sub> H<sub>2</sub>O/He</u>	<u>T<sub>H<sub>2</sub>O</sub> (°C)</u>	<u>Frequency (Hz)</u>	<u><math>\Delta</math></u>
20	-118	1.10	0.00854 ( $\Delta_0$ )
180	-121	1.11	0.02088
385	-120	1.10	0.02529
590	-120	1.10	0.02878
1200	-124	1.12	0.02998
1500	-122	1.10	0.03248
2000	-122	1.12	0.03248
3300	-121	1.11	0.03457
4600	-124	1.11	0.03469
6000	-120	1.10	0.03498
9000	-121	1.10	0.03492
> 10000	-119	1.10	0.03511 ( $\Delta_{\text{max}}$ )




Figure 1




Figure 2




Figure 3




Figure 4






Figure 5




Figure 6




Figure 7




Figure 8




Figure 9




Figure 10

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER Technical Report #14	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) A Water-Sensitive Thermomechanical Transition in a Polyimide		5. TYPE OF REPORT & PERIOD COVERED Technical Report Feb. 1977 to Feb. 1978
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) Y. Ozari, R. H. Chow and J. K. Gillham		8. CONTRACT OR GRANT NUMBER(s) N00014-76-C-0200
9. PERFORMING ORGANIZATION NAME AND ADDRESS Polymer Materials Program Department of Chemical Engineering ✓ Princeton University, Princeton, N. J. 08540		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS Task No. NR 356-504
11. CONTROLLING OFFICE NAME AND ADDRESS ✓ Office of Naval Research 800 North Quincy St., Arlington, Va. 22217		12. REPORT DATE February 1978
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		13. NUMBER OF PAGES 29
		15. SECURITY CLASS. (of this report)
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for Public Release; Distribution Unlimited		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number)  Polyimide Transitions Water		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number)  The effect of water vapor on a polyimide has been investigated in the temperature region -190° to 325°C using an automated torsion pendulum. A damping peak "H <sub>2</sub> O" develops at -122°C (1 Hz) in the thermomechanical spectra of the polymer <sup>2</sup> which is due to water-polymer interactions. The peak intensifies as the humidity of the conditioning atmosphere, at both 30°C and at 325°C, increases and attains a limiting value at about 2000 ppm <sub>v</sub> H <sub>2</sub> O. The process is reversible. It is concluded that the number of sites in <sup>2</sup> the		

polymer for interaction with water is low and limited ( $< 0.3$  molecules  $H_2O$  per polymer repeat unit) and, assuming direct proportionality between the intensity of the loss peak and the amount of water adsorbed, that the adsorption of water vapor follows the Langmuir isotherm.



# TECHNICAL REPORT DISTRIBUTION LIST

## No. Copies

## No. Copie

Dr. Stephen H. Carr  
Department of Materials Science  
Northwestern University  
Evanston, Illinois 60201

1

Dr. M. Broadhurst  
Bulk Properties Section  
National Bureau of Standards  
U.S. Department of Commerce  
Washington, D.C. 20234

2

Dr. C. H. Wang  
Department of Chemistry  
University of Utah  
Salt Lake City, Utah 84112

1

Dr. T. A. Litovitz  
Department of Physics  
Catholic University of America  
Washington, D.C. 20017

1

Dr. R. V. Subramanian  
Washington State University  
Department of Materials Science  
Pullman, Washington 99163

1

Dr. M. Shen  
Department of Chemical Engineering  
University of California  
Berkeley, California 94720

1

Dr. V. Stannett  
Department of Chemical Engineering  
North Carolina State University  
Raleigh, North Carolina 27607

1

Dr. D. R. Uhlmann  
Department of Metallurgy and Material Science  
Center for Materials Science and Engineering  
Massachusetts Institute of Technology  
Cambridge, Massachusetts 02139

Naval Surface Weapons Center  
White Oak  
Silver Spring, Maryland 20910  
Attn: Dr. J. M. Augl  
Dr. B. Hartman

1

Dr. G. Goodman  
Globe Union Inc.  
5757 North Green Bay Avenue  
Milwaukee, Wisconsin 53201

1

Picatinny Arsenal  
SMUPA-FR-M-D  
Dover, New Jersey 07801  
Attn: A. M. Anzalone  
Bldg. 3401

1

~~Dr. J. K. Gillham  
Princeton University  
Department of Chemistry  
Princeton, New Jersey 08540~~

1

Douglas Aircraft Co.  
3855 Lakewood Boulevard  
Long Beach, California 90846  
Attn: Technical Library  
C1 290/36-84  
ABTO-Sutton

1

Dr. E. Baer  
Department of Macromolecular Science  
Case Western Reserve University  
Cleveland, Ohio 44106

1

Dr. K. D. Pae  
Department of Mechanics and Materials Scienc.  
Rutgers University  
New Brunswick, New Jersey 08903

1

NASA-Lewis Research Center  
21000 Brookpark Road  
Cleveland, Ohio 44135  
Attn: Dr. T. T. Serofini, MS-49-1

1

Dr. Charles H. Sherman, Code TD 121  
Naval Underwater Systems Center  
New London, Connecticut

1

Dr. William Risen  
Department of Chemistry  
Brown University  
Providence, Rhode Island 02912

1

No. Copies

Dr. Alan Gent  
Department of Physics  
University of Akron  
Akron, Ohio 44304 1

Mr. Robert W. Jones  
Advanced Projects Manager  
Hughes Aircraft Company  
Mail Station D 132  
Culver City, California 90230 1

Dr. C. Giori  
IIT Research Institute  
10 West 35 Street  
Chicago, Illinois 60616 1

Dr. M. Litt  
Department of Macromolecular Science  
Case Western Reserve University  
Cleveland, Ohio 44106 1

Dr. R. S. Roe  
Department of Materials Science  
and Metallurgical Engineering  
University of Cincinnati  
Cincinnati, Ohio 45221 1

Dr. L. E. Smith  
U.S. Department of Commerce  
National Bureau of Standards  
Stability and Standards  
Washington, D.C. 20234 1

Dr. Robert E. Cohen  
Chemical Engineering Department  
Massachusetts Institute of Technology  
Cambridge, Massachusetts 02139 1

Dr. David Roylance  
Department of Materials Science and  
Engineering  
Massachusetts Institute of Technology  
Cambridge, Massachusetts 02039 1

No. Copies

Dr. W. A. Spitzig  
United States Steel Corporation  
Research Laboratory  
Monroeville, Pennsylvania 15146 1

Dr. T. P. Conlon, Jr., Code 3622  
Sandia Laboratories  
Sandia Corporation  
Albuquerque, New Mexico 87115 1

Dr. Martin Kaufmann, Head  
Materials Research Branch, Code 4542  
Naval Weapons Center  
China Lake, California 93555 1

Dr. T. J. Reinhart, Jr., Chief  
Composite and Fibrous Materials Branch  
Nonmetallic Materials Division  
Department of the Air Force  
Air Force Materials Laboratory (AFSC) 1  
Wright-Patterson Air Force Base, Ohio 45433

Dr. J. Lando  
Department of Macromolecular Science  
Case Western Reserve University  
Cleveland, Ohio 44106 1

Dr. J. White  
Chemical and Metallurgical Engineering  
University of Tennessee  
Knoxville, Tennessee 37916 1

Dr. J. A. Manson  
Materials Research Center  
Lehigh University  
Bethlehem, Pennsylvania 18015 1

Dr. R. F. Helmreich  
Contract RD&E  
Dow Chemical Co.  
Midland, Michigan 48640 1

Dr. R. S. Porter  
University of Massachusetts  
Department of Polymer Science and Engineering  
Amherst, Massachusetts 01002 1

# TECHNICAL REPORT DISTRIBUTION LIST

	<u>No. Copies</u>		<u>No. Copies</u>
Office of Naval Research Arlington, Virginia 22217 Attn: Code 472	2	Defense Documentation Center Building 5, Cameron Station Alexandria, Virginia 22314	12
Office of Naval Research Arlington, Virginia 22217 Attn: Code 102IP 1	6	U.S. Army Research Office P.O. Box 12211 Research Triangle Park, N.C. 27709 Attn: CRD-AA-IP	1
ONR Branch Office 536 S. Clark Street Chicago, Illinois 60605 Attn: Dr. Jerry Smith	1	Naval Ocean Systems Center San Diego, California 92152 Attn: Mr. Joe McCartney	1
ONR Branch Office 715 Broadway New York, New York 10003 Attn: Scientific Dept.	1	Naval Weapons Center China Lake, California 93555 Attn: Head, Chemistry Division	1
ONR Branch Office 1030 East Green Street Pasadena, California 91106 Attn: Dr. R. J. Marcus	1	Naval Civil Engineering Laboratory Port Hueneme, California 93041 Attn: Mr. W. S. Haynes	1
ONR Branch Office 760 Market Street, Rm. 447 San Francisco, California 94102 Attn: Dr. P. A. Miller	1	Professor O. Heinz Department of Physics & Chemistry Naval Postgraduate School Monterey, California 93940	1
ONR Branch Office 495 Summer Street Boston, Massachusetts 02210 Attn: Dr. L. H. Peebles	1	Dr. A. L. Slafkosky Scientific Advisor Commandant of the Marine Corps (Code RD-1) Washington, D.C. 20380	1
Director, Naval Research Laboratory Washington, D.C. 20390 Attn: Code 6100	1	Office of Naval Research Arlington, Virginia 22217 Attn: Dr. Richard S. Miller	1
The Asst. Secretary of the Navy (R&D) Department of the Navy Room 4E736, Pentagon Washington, D.C. 20350	1		
Commander, Naval Air Systems Command Department of the Navy Washington, D.C. 20360 Attn: Code 310C (H. Rosenwasser)	1		